

KS-50 WEATHERING POLYUREA TOP COATING



PRODUCT DESCRIPTION

Weathering polyurea top coating is a polyaspartate polyurea coating, its film does not contain photochromic and chromogenic molecule, which can completely avoid the shortcomings that aromatic isocyanate polymer is not resistant to ultraviolet light and easy to yellowing. It is an aliphatic, slow reaction, high performance material.

- Excellent weather resistance performance and not easy to yellowing, can expose for a long time.
- Good water resistance and good wear resistance with certain elasticity.
- The film is full of color and brilliance.
- Easy to construction.

TECHNICAL DATA BASED FOR REFERENCE

No.	ITEM	INDEX	TEST STANDARD
1	Tack free drying time/h	≤2	GB/T 1728-1989
2	Fully drying time /h	≤24	GB/T 1728-1989
3	Wear resistance (750g, 500r) /mg	≤40	GB/T 1768-1979
4	Adhesion (concrete substrate) /MPa	≥2.5	JC/T 2252-2014
5	Water resistance (720h)	No blistering, no wrinkling, no peeling, no obvious discoloration	JC/T 2252-2014
6	Anti-artificial climate accelerated test (1500h)	No obvious color change and powder, no bubbles and cracks.	GB/T 9274-1988

WHERE TO USE

It used for surface of concrete, steel structure, polyurea coating and other structures, also for the expose environment such as the landscape river course, water amusement park, building roof, etc.

CONSTRUCTION CONDITION

- Requirement for the substrate: The concrete substrate should be cleaned, repaired and polished to a certain roughness condition. After the enough time of maintenance, the concrete strength must be C25 or above, and moisture content should be less than 6%. When the substrate is ready, the next process should be carried out as soon as possible.
- Environmental temperature and humidity requirements: The construction environment temperature is between 5~35℃, and the substrate's temperature is at least 5℃ higher than the air temperature. The humidity range should be between 30~80%.
- Ventilation condition: Keep ventilation during construction, but don't construct the primer when there is strong wind.

CONSTRUCTION NOTES

- The component A and B should be stirred evenly before mixing them.
- The mixing ratio of component A and B by weight is A:B=3:1. It is ready to construct after it mixed evenly by 2~3 mins mechanically mixing,
- The mixed primer should be used up in 30min by roller or brusher or spraying. It is recommended mixing suitable quantity time by time according to the site construction. Any material is not allowed to add into the it to make it thinner.
- It can be applied layers according to the construction requirement. Normally, the next process should be carried out after the tack free time of the previous construction. If it is applied on the top of spraying polyurea coating or hand-applied polyurea coating, please apply it in 12~24 hours after the polyurea construction.

PROTECTION AND SECURITY

- Protective glasses, work clothes and shoes and hats are required for construction operations. During the construction, it is avoided contact with the skin, and once in contact with the skin, it is recommended to wash with warm water and detergent, if necessary, wash with a plastic brush or a steel ball. If inadvertently splashed into the eyes, need to wipe immediately and rinse with plenty of water, and go to the hospital for help.
- Normally, the fully dry coating is non-toxic and very safe.

RECOMMEND USAGE

Normally, the recommended usage is 0.15~0.3kg/m². The thickness of one construction is 0.15~0.25mm, and the thickness can be increased by multiple times construction. It is not allowed construct the thickness more than 0.25mm in one time.

PACKING

20kg/set, KS-50A: 15kg/pail; KS-50B: 5kg/pail

STORAGE AND TRANSPORTATION

- The coating should be sealed and stored in a dry, cool and well-ventilated condition, avoiding sun and rain and keeping away from fire.
- In the original packaging state and the prescribed storage conditions, the product has a shelf life of 6 months from the date of production.
- After open the drum, please use it as soon as possible and seal it again when not in use.
- The materials shall be stacked stationary and avoid violent collision when transporting.

ATTENTION

The information disclosed above is based on our knowledge and experience, and we believe it is correct and feasible. However, it must not be extended to the protection of end users, because the requirements of end users are related to many factors, which are closely related to correct design, construction, management, supervision, and so on. We will never be held responsible for incorrect using results and incorrect construction results, and we recommend that you perform relevant verifications before construction. If you have any questions, please contact Keshun Waterproof Technology Co., Ltd.



KESHUN WATERPROOF TECHNOLOGY CO., LTD (STOCK CODE: 300737)

Add: No.38-1, Hongqi Zhong Road, Ronggui, Shunde District, Foshan, Guangdong Province, China

KESHUN INTERNATIONAL LIMITED (HONG KONG OFFICE)

Add: 5301, 53/F. The Center 99 Queen's Road Central HK

Tel: 0086-757-28637166 | Email: sales@keshun.com.cn | Web: <https://cks.keshun.com.cn>

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.